



U.S. Army Research, Development and Engineering Command

The Validation and Approval of Chemical Agent Resistant Coatings



TECHNOLOGY DRIVEN. WARFIGHTER FOCUSED.

ASETSDefense 2012: Sustainable Surface Engineering for
Aerospace and Defense

August 28th, 2012

John A. Escarsega, Dawn M. Crawford & Fred Lafferman

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 28 AUG 2012		2. REPORT TYPE		3. DATES COVERED 00-00-2012 to 00-00-2012	
4. TITLE AND SUBTITLE The Validation and Approval of Chemical Agent Resistant Coatings				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U. S. Army Research Laboratory, Aberdeen Proving Ground, MD, 21005				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES ASETSDefense 2012: Sustainable Surface Engineering for Aerospace and Defense Workshop, August 27-30, 2012, San Diego, CA. Sponsored by SERDP/ESTCP.					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT Same as Report (SAR)	18. NUMBER OF PAGES 20	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

- ***Who We Are & What we Do***
- ***Standardization & Specifications***
- ***Technical Challenges***
- ***Selected CARC Efforts and discussions***
- ***Final Thoughts***



- **ARL is the Lead DOD R&D Activity for CARC**
 - Innovative formulations approaches
 - New raw materials selections
 - Advanced characterization

- **Maintains Ownership for all key specifications regarding pretreatments, primers and topcoats for all tactical and related support equipment and munition coatings.**

- ❖ ***Elements above assist to implement and transition products to the field.***

- **Develop materials for military unique coatings including pretreatments, primers, and topcoats**
 - Chemical Agent Resistant Coatings
 - Munitions coatings
 - Industrial coatings for vehicle interiors
- **Implement and transition new products**
 - Specifications and Standards
 - Troubleshooting, consulting, and problem solving
- **Analyze and solve technical problems related to coatings systems used on Army Materiel**

Implementation

Environmental

Survivability



Durability

- Every item that the Army fields starts with a document, namely a specification. Multiple specifications may be required to define a specific item along with a standard on how to process the item.
 - Cleaning Methods
 - Pretreatment Methods
 - Anticorrosive Primers
 - Chemical Agent Resistant Coating (CARC) Topcoat

**Governed by application and inspection specification,
MIL-DTL-53072.**

- Step 1 – Planning
- Step 2 – Research & Development
- Step 3 – Approval and Publication


- Reasons for development or revision of specifications:
 - Environmental regulations (Hexavalent Chromate and HAPs)
 - Performance requirements
 - Advances in new technology
 - **Major gaps in technology**

- Uniqueness of Coating and Corrosion Team Specifications:
 - Notarized Statements of Composition


- Transition document for military to use in contracts

Hierarchical Architecture of Multifunctional Coatings


Today



Tomorrow





Individual Coating Components



- Hexavalent Chromium Free Pretreatments for various substrates.*
- Alternatives to Isocyanate Based Topcoats*
- Elimination of Silica Flattened topcoats
- New Chemical Agent Testing Methodologies
- Alternatives to conventional cure

Polymeric beads

Army will
Discontinue use
of Silica based
topcoats



• Integrated within Film


- Polymeric beads
 - Reduce chalking effect
 - Improve UV resistance
 - Improve performance



Diatomaceous silica

Talc

Q-Lab Arizona, Accelerated Outdoor Weathering Results




- **Superior weather resistance—Minimal chalking and color degradation.**
- **Survivability—Spectral and specular reflection not affected by weathering. Infrared not affected during weathering.**
- **Superior mar resistance.**
- **Less paint weight- 20-25%**
- **Less paint usage—Documented by Star4D and Sikorsky Helicopter—10-15%. Confirmed by industry and depots.**
- **Health and safety—No crystalline silica exposure during repair, sanding and removal operations.**
- **Longer service life—less cost for repainting.**

Raw Material Selection


Resin




Pigments



Polymeric
Flattening
Agents




Additives




Solvents




Tailored Coating



Providing Agent Resistance




Surface Enhanced



In situ Cross-Linked


Two Fold Approach :
Incorporating
chemistries to actively
bind and crosslink to
create barrier
properties and support
decontamination
through additional
surface modifications





Reduce Dry to Fly Time


- OEM's and Depot's define production delays as a critical gap
- UV cure chemistry enables handling in 10 minutes vs. 6-8 hours (standard cure)
- Reduce VOC's
- Highly adaptable and relevant for field repairs




2K Water Dispersible Paint with
UV active additives




1. Mix and spray the same as MIL-DTL-64159
2. Allow 10 minute of flash off for evaporation



3. 10 minute cure process using H & S Auto Shot 1200W UVA lamp



**UH-60 rotor blade section
coated with black rapid cure
CARC. Cured with two
1200W UVA lamps in
tandem.**



- Patent Application Filed
- Formulations completed for green and black using low solar absorbing (LSA) pigmentation
- Optimized UV irradiance requirements for rapid cure (8 inch stand-off distance/ 10 minutes of UVA light exposure). Panel results show “set to handle” properties after 10 minutes following UV cure, dry hard property after 30 minutes following UV cure and MEK resistance in less than 24 hours.
- Demonstrated success of UV cure CARC on small section of UH-60 and CH-47 rotor blades.

- Technology Gaps/Accomplishments are continually evolving.
- Our successes will be with the continued collaborations with our services, industry and academia.
- Our specification and technical manuals will define the requirements and processes.
- It is within this framework that the path will be most clear and straight forward.